



Technical Data

Product: MOBI CARE EMULSION

Description

Mobi Care Emulsion Paint is a premium solution that adds a touch of elegance and durability to interior walls. With its smooth application and wide range of vibrant colors, Mobi Care Emulsion Paint transforms any space into a visually stunning and long-lasting environment.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior Water Base Primer / MOBI Oil Base Primer, fill the surface with Mobi Fine Filler/Wall Putty/Care Putty. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer & Mobi Fine Filler/Wall Putty/Care Putty for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with Water Base Primer / MOBI Oil Base Primer and then fill any surface imperfections with the Mobi Fine Filler/Wall Putty/Care Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water

Solid content by volume (%)

: 65 ± 5 %

Colors

: As per shade card

Film Thickness

: Not Applicable

Drying Time at 25°C

: 1-2 Hours

Recoat at 25°C

: 3-4 Hours

Ph

: 8.5 – 9.5

Pack Viscosity

: 22 – 32 Poise

Specific Gravity

: 1.50 – 1.62 (Depending Upon Colors)

No of Coats

: 2 – 3 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.

Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646



E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI CARE EMULSION

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 120 - 140 Square foot /liter/coat depending upon surface profile
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	3.64 Liter , 14.56 Liter

Recommended System: Powdery Surface

- 1coat MOBI MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Care Emulsion (2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Care Emulsion (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- Mobi Fine Filler/Wall Putty/Care Putty as and where required.
- MOBI Care Emulsion (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL EMULSION

Description

Mobi Wall Emulsion is an excellent quality emulsion with improved coverage, binding and finish. It is specially developed for all interior surfaces including brick work, plaster, cement & wall boards.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior Water Base Primer / MOBI Oil Base Primer, fill the surface with Mobi Fine Filler/Wall Putty/Care Putty. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer & Mobi Fine Filler/Wall Putty/Care Putty for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer and then fill any surface imperfections with the Mobi Fine Filler/Wall Putty/Care Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water

Solid content by volume (%)	:	65 ± 5 %
Colors	:	As per shade card
Film Thickness	:	Not Applicable
Drying Time at 25°C	:	1-2 Hours
Recoat at 25°C	:	3-4 Hours
Ph	:	8.5 – 9.5
Pack Viscosity	:	28 - 38 Poise
Specific Gravity	:	1.50 – 1.62 (Depending Upon Colors)
No of Coats	:	2 – 3 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL EMULSION

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 130 - 150 Square foot /liter/coat depending upon surface profile
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	3.64 Liter , 14.56 Liter

Recommended System: Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Wall Emulsion (2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Wall Emulsion (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- Mobi Fine Filler/Wall Putty/Care Putty as and where required.
- MOBI Wall Emulsion (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SUPER EMULSION

Description

MOBI SUPER EMULSION is a PVA Co-Polymer based excellent quality emulsion for all normal interior masonry surfaces including brick work, plaster, cement rendering and wall boards. A blend of selective pigments, extenders and additives in special selective ratio makes its quality. It has good adhesion on suitably prepared surfaces with better hiding and coverage. MOBI Super Emulsion is recommended only on interior surfaces.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior Water Base Primer / MOBI Oil Base Primer, fill the surface with Mobi Fine Filler/Wall Putty/Care Putty. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer & Mobi Fine Filler/Wall Putty/Care Putty for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer and then fill any surface imperfections with the Mobi Fine Filler/Wall Putty/Care Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water

Solid content by volume (%) : 65 ± 5 %

Colors : As per shade card

Film Thickness : Not Applicable

Drying Time at 25°C : 1-2 Hours

Recoat at 25°C : 3-4 Hours

Ph : 8.5 – 9.5

Pack Viscosity : 28 - 38 Poise

Specific Gravity : 1.50 – 1.62 (Depending Upon Colors)

No of Coats : 2 – 3 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SUPER EMULSION

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 120 - 140 Square foot /liter/coat depending upon surface profile
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	0.91 Liter, 3.64 Liter , 14.56 Liter

Recommended System: Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Super Emulsion (2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Super Emulsion (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- Mobi Fine Filler/Wall Putty/Care Putty as and where required.
- MOBI Super Emulsion (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI STAIN REMOVER

Description

MOBI STAIN REMOVER is a specially formulated acrylic emulsion with outstanding quality for interior surfaces application. It is low VOC interior premium paint specially formulated to repel the stains like, ketchup, coffee, juice, and handprints etc. Stains can be removed without damaging the paint film. It has excellent brush ability, flow, leveling, wash ability, smooth finish, color fastness, beautiful low sheen and long lasting durability. MOBI Stain remover offers good hiding and maximum protection to masonry surfaces including brickwork plaster cement and wall boards.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior Water Base Primer / MOBI Oil Base Primer, fill the surface with Mobi Fine Filler/Wall Putty/Care Putty. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer & Mobi Fine Filler/Wall Putty/Care Putty for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer and then fill any surface imperfections with the Mobi Fine Filler/Wall Putty/Care Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	50 ± 5 %
Colors	:	As per shade card
Film Thickness	:	Not Applicable
Drying Time at 25°C	:	1-2 Hours
Recoat at 25°C	:	3-4 Hours
Ph	:	8.5 – 9.5
Pack Viscosity	:	4 - 6 Poise
Specific Gravity	:	1.28 – 1.34 (Depending Upon Colors)
No of Coats	:	3 – 4 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI STAIN REMOVER

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 100 - 130 Square foot /liter/coat depending upon surface profile
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 1-2 parts of clean water to 4 parts of paint (25-50%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	1 Liter, 4 Liter , 16 Liter

Recommended System: Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Stain Remover(2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Stain Remover (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- Mobi Fine Filler/Wall Putty/Care Putty as and where required.
- MOBI Stain Remover (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI PLASTIC EMULSION

Description

MOBI PLASTIC EMULSION is an excellent quality acrylic based paint suitable for all types of interior masonry surfaces. Its a blend of selective pigments, extenders and additives. It is easy to clean, extra smooth and has a silky feel. All these attributes differentiate MOBI Plastic Emulsion from other brands available in this category.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior Water Base Primer / MOBI Oil Base Primer, fill the surface with Mobi Fine Filler/Wall Putty/Care Putty. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer & Mobi Fine Filler/Wall Putty/Care Putty for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer and then fill any surface imperfections with the Mobi Fine Filler/Wall Putty/Care Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water

Solid content by volume (%)	:	65 ± 5 %
Colors	:	As per shade card
Film Thickness	:	Not Applicable
Drying Time at 25°C	:	1-2 Hours
Recoat at 25°C	:	3-4 Hours
Ph	:	8.5 – 9.5
Pack Viscosity	:	16 - 22 Poise
Specific Gravity	:	1.38 – 1.45 (Depending Upon Colors)

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI PLASTIC EMULSION

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 120 - 130 Square foot /liter/coat depending upon surface profile
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	1 Liter, 4 Liter , 16 Liter

Recommended System: Powdery Surface

- 1coat MOBI MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Plastic Emulsion(2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- MOBI Plastic Emulsion (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- Mobi Fine Filler/Wall Putty/Care Putty as and where required.
- MOBI Plastic Emulsion (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WEATHER SAFE

Description

MOBI WEATHER SAFE is a specially formulated emulsion with outstanding quality for exterior surfaces application. It gives tough & durable exterior coating suitable for all weather conditions. A blend of selective pigment, extenders and additives make it a brand top of its class. It has color lock technology.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior & Exterior Primer / MOBI Exterior Primer, fill the surface if required with Mobi Exterior Fine Filler. Please refer to TDS of MOBI Interior MOBI Interior & Exterior Primer / MOBI Exterior Primer & Mobi Exterior Fine Filler for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior & Exterior Primer / MOBI Exterior Primer and then fill any surface imperfections with the Mobi Exterior Fine Filler. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	65 ± 5 %
Colors	:	As per shade card
Film Thickness	:	Not Applicable
Drying Time at 25°C	:	1-2 Hours
Recoat at 25°C	:	3-4 Hours
Ph	:	8.5 – 9.5
Pack Viscosity	:	16 - 22 Poise
Specific Gravity	:	1.36 – 1.5 (Depending Upon Colors)
No of Coats	:	3 – 4 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WEATHER SAFE

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 130 - 150 Square foot /liter/coat depending upon surface profile.
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	1 Liter, 4 Liter , 16 Liter

Recommended System: Powdery Surface

- 1coat MOBI Interior & Exterior Primer / MOBI Exterior Primer.
- 1 thin coat Mobi Exterior Fine Filler.
- MOBI Weather Safe(2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior & Exterior Primer / MOBI Exterior Primer.
- 1 thin coat Mobi Exterior Fine Filler.
- MOBI Weather Safe (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- 1 thin coat Mobi Exterior Fine Filler if and where required.
- MOBI Weather Safe (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WEATHER PLUS

Description

MOBI WEATHER PLUS is high quality acrylic based emulsion paint for new or previously painted exterior masonry surfaces. Because of its outstanding resistance to weathering, it is perfect for protection, decoration and long lasting finish of all masonry surfaces such as brick work, plaster and cement rendering.

SURFACE PREPARATION:

Surfaces must be clean, dry, free from masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

Filling New Surfaces:

After priming new surfaces with MOBI Interior & Exterior Primer / MOBI Exterior Primer, fill the surface if required with Mobi Exterior Fine Filler. Please refer to TDS of MOBI Interior MOBI Interior & Exterior Primer / MOBI Exterior Primer & Mobi Exterior Fine Filler for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior & Exterior Primer / MOBI Exterior Primer and then fill any surface imperfections with the Mobi Exterior Fine Filler. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	65 ± 5 %
Colors	:	As per shade card
Film Thickness	:	Not Applicable
Drying Time at 25°C	:	1-2 Hours
Recoat at 25°C	:	3-4 Hours
Ph	:	8.5 – 9.5
Pack Viscosity	:	16 - 22 Poise
Specific Gravity	:	1.36 – 1.5 (Depending Upon Colors)
No of Coats	:	3 – 4 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WEATHER PLUS

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 130 - 150 Square foot /liter/coat depending upon surface profile.
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	1 Liter, 4 Liter , 16 Liter

Recommended System: Powdery Surface

- 1coat MOBI Interior & Exterior Primer / MOBI Exterior Primer.
- 1 thin coat Mobi Exterior Fine Filler.
- MOBI Weather Plus(2 or more coat)

Recommended System: Alkaline & New Surface

- 1coat MOBI Interior & Exterior Primer / MOBI Exterior Primer.
- 1 thin coat Mobi Exterior Fine Filler.
- MOBI Weather Plus (2 or more coat)

Normal Sound surface previously painted:

- No Primer required.
- 1 thin coat Mobi Exterior Fine Filler if and where required.
- MOBI Weather Plus (2 or more coat)

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability, 18 Months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI FINE FILLER

Description

MOBI FINE FILLER (water based) is a ready to use filler that has an excellent whiteness, coverage and application properties. Its high quality filling properties has made it ideal for use on all types of interior masonry surfaces. It provides a smooth base for the application of all MOBI Interior Topcoats.

SURFACE PREPARATION:

Allow all new surfaces to dry out completely. Surface must be clean, dry & free of all masonry salts .Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

New Surfaces:

Prime new surfaces with 1 coat of MOBI Interior Water Base Primer / MOBI Oil Base Primer. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer before applying MOBI fine filler.

TECHNICAL DATA

TYPE	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	High solid putty
Film Thickness		
Ph	:	8.5 – 9.5
Gel Strength	:	160-180 GM/CM3 @30C
Drying Time at 25°C	:	2-3 Hours
Recoat at 25°C	:	4-6 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 40-50 square Feet /Kg/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY


8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI FINE FILLER

TECHNICAL DATA

Application	:	Scraper or Putty Applicator 
Thinning	:	Ready to use.
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	5 Kg , 20 Kg

Recommended System:

Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler.
- 2 or more coats any of MOBI interior top coat.

Recommended System:

Alkaline & New Surface

- 1coat MOBI MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Fine Filler.
- 2 or more coats any of MOBI interior top coat.

Normal Sound surface previously painted:

- No primer required.
- 2-3 coats MOBI Fine Filler where required.
- 2 or more coats any of MOBI interior top coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL PUTTY

Description

MOBI WALL PUTTY (water based) is a ready to use filler. It gives a smooth and brilliant white base by filling the pores. It is easy to apply and quick in drying. Its excellent filling properties give a smooth finish for topcoat application. MOBI Wall Putty is recommended to use only on interior surfaces.

SURFACE PREPARATION:

Allow all new surfaces to dry out completely. Surface must be clean, dry & free of all masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

New Surfaces:

Prime new surfaces with 1 coat of MOBI Interior Water Base Primer / MOBI Oil Base Primer. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer before applying MOBI Wall Putty.

TECHNICAL DATA

TYPE	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	High solid putty
Film Thickness		
Ph	:	8.5 – 9.5
Gel Strength	:	160-180 GM/CM3 @30C
Drying Time at 25°C	:	2-3 Hours
Recoat at 25°C	:	4-6 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 40-50 square Feet /Kg/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY


8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL PUTTY

TECHNICAL DATA

Application	:	Scraper or Putty Applicator 
Thinning	:	Ready to use.
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	5 Kg , 20 Kg

Recommended System:
Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Wall Putty.
- 2 or more coats any of MOBI interior top coat.

Recommended System:
Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Wall Putty.
- 2 or more coats any of MOBI interior top coat.

Normal Sound surface previously painted:

- No primer required.
- 2-3 coats MOBI Wall Putty where required.
- 2 or more coats any of MOBI interior top coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should be made. Storage stability 18 months when stored properly in original sealed container at 15-35°C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI CARE PUTTY

Description

MOBI CARE PUTTY (water based) is an economical ready to use filler. It gives a smooth and brilliant white base by filling the pores. It is easy to apply and quick in drying. It gives a smooth finish for topcoat application. MOBI Care Putty is recommended to use only on interior surfaces.

SURFACE PREPARATION:

Allow all new surfaces to dry out completely. Surface must be clean, dry & free of all masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

New Surfaces:

Prime new surfaces with 1 coat of MOBI Interior Water Base Primer / MOBI Oil Base Primer. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer before applying MOBI Care Putty.

TECHNICAL DATA

TYPE	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	High solid putty
Film Thickness		
Ph	:	8.5 – 9.5
Gel Strength	:	150-170 GM/CM3 @30C
Drying Time at 25°C	:	2-3 Hours
Recoat at 25°C	:	4-6 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 40-50 square Feet /Kg/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY


8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI CARE PUTTY

TECHNICAL DATA

Application	:	Scraper or Putty Applicator 
Thinning	:	Ready to use.
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	,20 Kg

Recommended System:

Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Care Putty.
- 2 or more coats any of MOBI interior top coat.

Recommended System:

Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Care Putty.
- 2 or more coats any of MOBI interior top coat.

Normal Sound surface previously painted:

- No primer required.
- 2-3 coats MOBI Care Putty where required.
- 2 or more coats any of MOBI interior top coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI PRIMER SHEESHA PUTTY

Description

MOBI PRIMER SHEESHA PUTTY (water based) is a premium quality ready to use filler. It gives a smooth and brilliant white base by filling the pores. It is easy to apply and quick in drying. This putty is formulated to retain a strong adhesion on the wall surface. It provides a very strong, durable base that provides an ideal finish for subsequent coats.

SURFACE PREPARATION:

Allow all new surfaces to dry out completely. Surface must be clean, dry & free of all masonry salts. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

New Surfaces:

Prime new surfaces with 1 coat of MOBI Interior Water Base Primer / MOBI Oil Base Primer. Please refer to TDS of MOBI Interior Water Base Primer / MOBI Oil Base Primer for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Interior Water Base Primer / MOBI Oil Base Primer before applying MOBI Primer Sheesha Putty.

TECHNICAL DATA

TYPE	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	High solid putty
Film Thickness		
Ph	:	8.5 – 9.5
Gel Strength	:	140-160 GM/CM3 @30C
Drying Time at 25°C	:	2-3 Hours
Recoat at 25°C	:	4-6 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 40-50 square Feet /Kg/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY


8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI PRIMER SHEESHA PUTTY

TECHNICAL DATA

Application	:	Scraper or Putty Applicator 
Thinning	:	Ready to use.
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	5Kg ,20 Kg

Recommended System:
Alkaline & New Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Primer Sheesha Putty.
- 2 or more coats any of MOBI interior top coat.

Recommended System:
Powdery Surface

- 1coat MOBI Interior Water Base Primer / MOBI Oil Base Primer
- 2-3 coats Mobi Primer Sheesha Putty..
- 2 or more coats any of MOBI interior top coat.

Normal Sound surface previously painted:

- No primer required.
- 2-3 coats Mobi Primer Sheesha Putty.
- where required.
- 2 or more coats any of MOBI interior top coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR FINE FILLER

Description

MOBI EXTERIOR FINE FILLER (water based) Filler is a high quality acrylic based fine filler for all types of exterior masonry surfaces such as brickwork, plaster and cement. It is ready to use and easy to apply. It gives smooth finish for top coat. Mobi Exterior Fine Filler is recommended to use only exterior surfaces.

SURFACE PREPARATION:

Allow all new surfaces to dry out completely. Surface must be clean, dry & free of all masonry salts .Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush. Treat any area affected by mould, lichens, algae or moss with bleach. Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dust off.

New Surfaces:

Prime new surfaces with 1 coat of MOBI Exterior Wall Primer. Please refer to TDS of MOBI Exterior Wall Primer for correct application procedure and drying time properties.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes & cracks use sand and cement mixture. Allow to dry. Prime the surface with MOBI Exterior Wall Primer before applying MOBI Exterior Fine Filler.

TECHNICAL DATA

TYPE	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water
Solid content by volume (%)	:	70 ± 5
Film Thickness		
Ph	:	8.5 – 9.5
Gel Strength	:	150 - 170 GM/CM3 @30C
Drying Time at 25°C	:	2-3 Hours
Recoat at 25°C	:	4-6 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 50-70 square Feet /Kg/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY


8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR FINE FILLER

TECHNICAL DATA

Application	:	Scrapper or Putty Applicator 
Thinning	:	Ready to use.
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	5 Kg, 20 Kg

Recommended System:

Alkaline & New Surface

- 1 coat MOBI Exterior Wall Primer
- 1 coat Mobi Exterior Fine Filler.
- 2 or more coats any of MOBI Exterior top coat.

Recommended System:

Powdery Surface

- 1 coat MOBI Exterior Wall Primer
- 1 coat Mobi Exterior Fine Filler.
- 2 or more coats any of MOBI Exterior top coat.

Normal Sound surface previously painted:

- 1 coat MOBI Exterior Wall Primer
- 1 coat Mobi Exterior Fine Filler where required.
- 2 or more coats any of MOBI Exterior top coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should be made. Storage stability 18 months when stored properly in original sealed container at 15-35°C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SUPER PRIMER

Description

MOBI Super Primer is an economical primer for masonry surfaces. It is ideal for all types of interior surfaces such as plaster brickwork or cement rendering. It is an excellent sealing primer, which provides good adhesion both for the surface and top coat.

New Surface:

New surfaces must be clean, dry and free from masonry salts. Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper or stiff brush and dust off. Treat any area affected by mould, lichens, algae or moss with bleach. Now Prime the new surface with MOBI Super Primer. Let it dry for 2-3 hours and then smooth the surface with Mobi Fine Filler/Wall Putty/Care Putty.

Repaint for Sound Surface:

Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper and dust off. Prime and fill the surface as described above.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes and cracks, use sand and cement mixture. Allow it to dry. Now prime the surface with MOBI Super Primer and then fills the surface imperfections with Mobi Fine Filler/Wall Putty/Care Putty as described above

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	PVA Co-Polymer
Solvent	:	Water

Solid content by volume (%) : 65 ± 5 %

Colors : White

Film Thickness : Not Applicable

Drying Time at 25°C : 1-2 Hours

Recoat at 25°C : 3-4 Hours

Ph : 8.5 – 9.5

Pack Viscosity : 18 - 22 Poise

Specific Gravity : 1.5 ± 0.1

No of Coats : 1 - 2 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.





8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
 Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
 E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SUPER PRIMER

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 100 - 130 Square foot /liter/coat depending upon surface profile.
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	3.64 Liter , 14.56 Liter

Recommended System: Alkaline & New Surface

- 1 -2 coat MOBI Super Primer.
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- 2 or More Coats of any of MOBI Interior Emulsion.

Recommended System: Powdery Surface

- 1 -2 coat MOBI Super Primer.
- 2-3 coats Mobi Fine Filler/Wall Putty/Care Putty.
- 2 or More Coats of any of MOBI Interior Emulsion.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR & INTERIOR PRIMER

Description

MOBI Exterior & Interior Primer is a high quality acrylic based alkali resistant primer for masonry surfaces. It is ideal for all types of interior and exterior surfaces such as plaster brickwork or cement rendering. It is an excellent sealing primer, which provides good adhesion both for the surface and top coat.

New Surface:

New surfaces must be clean, dry and free from masonry salts. Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper or stiff brush and dust off. Treat any area affected by mould, lichens, algae or moss with bleach. Now prime the new surface with MOBI Exterior & Interior Primer. Let it dry for 2-3 hours and then smooth the surface with Mobi Fine Filler/Wall Putty/Care Putty.

Repaint for Sound Surface:

Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper and dust off. Prime and fill the surface as described above.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes and cracks, use sand and cement mixture. Allow it to dry. Now prime the surface with MOBI Exterior & Interior Primer and then fills the surface imperfections with Mobi Fine Filler/Wall Putty/Care Putty as described above

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water

Solid content by volume (%) : 65 ± 5 %

Colors : White

Film Thickness : Not Applicable

Drying Time at 25°C : 1-2 Hours

Recoat at 25°C : 3-4 Hours

Ph : 8.5 – 9.5

Pack Viscosity : 18 - 22 Poise

Specific Gravity : 1.45 ± 0.05

No of Coats : 1 - 2 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR & INTERIOR PRIMER

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 100 - 130 Square foot /liter/coat depending upon surface profile.
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	3.64 Liter , 14.56 Liter

Recommended System: Powdery Surface

- 1-2 coat MOBI Exterior & Interior Primer
- 1-2 coats MOBI Exterior/ Interior Fine Filler.
- 2 or more coats of MOBI Finishing Coat Interior / Exterior

Recommended System: Alkaline & New Surface

- 1-2 coat MOBI Exterior & Interior Primer
- 1-2 coats MOBI Exterior/ Interior Fine Filler.
- 2 or more coats of MOBI Finishing Coat Interior / Exterior

Normal Sound surface previously painted:

- 1-2 coat MOBI Exterior & Interior Primer if required.
- 1-2 coats MOBI Exterior/ Interior Fine Filler.
- 2 or more coats of MOBI Finishing Coat Interior / Exterior

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR PRIMER

Description

MOBI Exterior Primer is a high quality acrylic based alkali resistant primer for masonry surfaces. It is ideal for all types of exterior surfaces such as plaster brickwork or cement rendering. It is an excellent sealing primer, which provides good adhesion both for the surface and top coat.

New Surface:

New surfaces must be clean, dry and free from masonry salts. Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper or stiff brush and dust off. Treat any area affected by mould, lichens, algae or moss with bleach. Now prime the new surface with MOBI Exterior Primer. Let it dry for 2-3 hours and then smooth the surface with Mobi Exterior Fine Filler.

Repaint for Sound Surface:

Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper and dust off. Prime and fill the surface as described above.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes and cracks, use sand and cement mixture. Allow it to dry. Now prime the surface with MOBI Exterior Primer and then fills the surface imperfections with Mobi Exterior Fine Filler as described above

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Acrylic Co-Polymer
Solvent	:	Water

Solid content by volume (%) : 65 ± 5 %

Colors : White

Film Thickness : Not Applicable

Drying Time at 25°C : 1-2 Hours

Recoat at 25°C : 3-4 Hours

Ph : 8.5 – 9.5

Pack Viscosity : 18 - 22 Poise

Specific Gravity : 1.45 ± 0.05

No of Coats : 1 - 2 Coats

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI EXTERIOR PRIMER

TECHNICAL DATA

Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 100 - 130 Square foot /liter/coat depending upon surface profile.
Application	:	Brush,  Roller 
Thinning	:	
Brush or Roller	:	For application thinning should not exceed 2-3 parts of clean water to 4 parts of paint (50-75%).
Cleaning	:	Clean all equipment with water immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	3.64 Liter , 14.56 Liter

Recommended System: Powdery Surface

- 1-2 coat MOBI Exterior Primer
- 1-2 coats MOBI Exterior Fine Filler.
- 2 or more coats of MOBI Finishing Coat Exterior

Recommended System: Alkaline & New Surface

- 1-2 coat MOBI Exterior Primer
- 1-2 coats MOBI Exterior fine Filler.
- 2 or more coats of MOBI Finishing Coat Exterior

Normal Sound surface previously painted:

- 1-2 coat MOBI Exterior Primer if required.
- 1-2 coats MOBI Exterior Fine Filler.
- 2 or more coats of MOBI Finishing Coat Exterior

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL SEALER

Description

MOBI WALL SEALER is top quality wall sealer made from highest quality resin and pigment with carefully selected fillers. Mobi Wall Sealer is specially formulated to protect and seal the surface. It reduces damaged produced by alkali and salts. It gives smooth finish and better coverage to topcoat. It can be apply on all interior surfaces.

SURFACE PREPARATION:

New Surface:

New surfaces must be clean, dry and free from masonry salts. Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper or stiff brush and dust off. Treat any area affected by mould, lichens, algae or moss with bleach. Prime the new surface with MOBI Wall Sealer and let it dry overnight and then smooths the surface with Mobi Fine Filler/Wall Putty/Care Putty.

Repaint for Sound Surface:

Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper and dust off. Prime and fill the surface as described above.

Powdery, Dusty Surfaces, Defects, Cracks & Other Surfaces:

Repair minor defects. For large holes and cracks, use sand and cement mixture. Allow it to dry. Prime the surface with MOBI Wall Sealer and then fills the surface imperfections with Mobi Fine Filler/Wall Putty/Care Putty.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	White only
Film Thickness	:	Wet : 50-55 micrometers. Dry : 25-30 micrometers.

Pack Viscosity	:	15 – 18 Poise
Specific Gravity	:	1.45 ± 0.05
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WALL SEALER

TECHNICAL DATA

Application

:

Brush,



Roller



Spray



Thinning

:

Add up to 2 parts of white spirit to 4 parts of paints (50%).

Brush or Roller

Conventional Spray

:

Add up to 2 parts of white spirit to 4 parts of paint (50%)

Cleaning

:

Clean all equipment with white spirit or Kerosene immediately after use.

Finish

:

Smooth Matt Finish

Pack Size

:

0.91 , 3.64 , 14.56 Liter

Recommended System:

Alkaline & New Surface

- 1 – 2 coats Mobi Wall Sealer.
- 1-2 coats Mobi Fine Filler /Wall Putty/Care Putty
- 2 or more coats of Mobi Finishing Coat.

Recommended System:

Powdery Surface

- 1 – 2 coats Mobi Wall Sealer.
- 1-2 coats Mobi Fine Filler /Wall Putty/Care Putty
- 2 or more coats of Mobi Finishing Coat.

Normal Sound surface previously painted:

- 1 coat Mobi Wall Sealer if required.
- 1-2 coats Mobi Fine Filler /Wall Putty/Care Putty
- 2 or more coats of Mobi Finishing Coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.

Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646

E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI UNDERCOAT WHITE

Description

MOBI UNDERCOAT WHITE is a high quality solvent base alkali resistant primer for sealing timber or wood surfaces. It is an excellent sealing primer, which provides good adhesion both for the surface and top coat.

SURFACE PREPARATION:

New Surface:

New surface must be clean and free from Oil, Grease and Dust.

Repaint:

Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids : 50 ± 10 %

Colors : White only

Film Thickness : Wet : 50-55 micrometers.
Dry : 20-25 micrometers.

Pack Viscosity : 15 – 18 Poise

Specific Gravity : 1.45 ± 0.05

Drying Time at 25°C : 5-6 Hours

Recoat at 25°C : 16 Hours

Practical Coverage : A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI UNDERCOAT WHITE

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 2 parts of white spirit to 4 parts of paints (50%).
Conventional Spray	:	Add up to 2 parts of white spirit to 4 parts of paint (50%)
Cleaning	:	Clean all equipment with white spirit or Kerosene immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	0.91 , 3.64 , 14.56 Liter

Recommended System:

New Surface

- 1 – 2 coats Mobi Under Coat White.
- 2 or more coats of Mobi Finishing Coat.

Normal Sound surface previously painted:

- 1 -2 coast Mobi Under Coat White if required.
- 2 or more coats of Mobi Finishing Coat.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI RED OXIDE PRIMER

Description

MOBI RED OXIDE PRIMER is used in industries and homes to protect the ferrous surface from corrosion. Due to its excellent decorative as well as protective qualities, it also recommended to be used on a variety of Industrial Appliances and Machines. MOBI Red Oxide Primer is composed of a blend of specially designed Resin with non-corrosion pigment and inert extenders which impart it exclusive properties of corrosion resistance, adhesion and colorfastness coupled with mild chemical and good environment resistance.

SURFACE PREPARATION:

New Surface:

Surface should be free from all contaminations such as oil, grease, mill scale and rust. Oil and grease should be removed by degreasing solution or cleaning solvents. Mill scale and rust should be removed by chipping or sand blasting.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Anti Corrosive Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	Red Oxide
Film Thickness	:	Dry : 35 ± 5 microns.
Pack Viscosity	:	14 – 18 Poise
Specific Gravity	:	1.40 ± 0.05
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 120 -180 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI RED OXIDE PRIMER

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 2 parts of white spirit to 4 parts of paints (50%).
Conventional Spray	:	Add up to 2 parts of white spirit to 4 parts of paint (50%)
Cleaning	:	Clean all equipment with white spirit or Kerosene Immediately after use.
Finish	:	Smooth Matt Finish
Pack Size	:	0.91Liter, 3.64Liter , 14.56 Liter

Recommended System:

New Surface

- 1 – 2 coats Mobi Red Oxide Primer.
- 2 or more coats of Mobi Synthetic Enamel/ Matt Enamel/ Metallic Enamel.

Normal Sound surface previously painted:

- 1 – 2 coats Mobi Red Oxide Primer.
- 2 or more coats of Mobi Synthetic Enamel/ Matt Enamel/ Metallic Enamel.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SYNTHETIC ENAMEL

Description

MOBI Synthetic Enamel is high quality enamel that has no comparison because of its long lasting finish and durability. MOBI Synthetic Enamel is designed to be applied on primed Ferrous , wooden and nonferrous surface. It is suitable for all types of interior and exterior metal and wooden surfaces.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties now apply 2-3 coats of Mobi Synthetic Enamel.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Undercoat White and then fill any surface imperfections with Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids : 50 ± 10 %

Colors : All Colors from shade card.

Film Thickness : Dry : 35 ± 5 microns.

Pack Viscosity : 6 – 8 min @ ford cup F4

Specific Gravity : 1 ± 0.1 Depending upon colors

Drying Time at 25°C : 5-6 Hours

Recoat at 25°C : 16 Hours

Practical Coverage : A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SYNTHETIC ENAMEL

TECHNICAL DATA

Application

:

Brush,



Roller



Spray



Thinning

:

Add up to 2 parts of white spirit to 4 parts of paints (50%).

Brush or Roller

Conventional Spray

:

Add up to 2 parts of white spirit to 4 parts of paint (50%)

Cleaning

:

Clean all equipment with white spirit or Kerosene Immediately after use.

Finish

:

Smooth Glossy Finish.

Pack Size

:

0.91Liter, 3.64Liter , 14.56 Liter

Recommended System:

General Steel Surface

- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI Synthetic Enamel.

Recommended System:

Galvanized Surface or Non Ferrous

- One coat wash primer
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI Synthetic Enamel.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White.
- 2 -3 Coats MOBI Synthetic Enamel.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.

Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646

E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI METALLIC ENAMEL

Description

MOBI Metallic Enamel is a high quality solvent-based metallic finish, suitable for use on all types of interior and exterior wood and metal surfaces. **MOBI** Metallic Enamel gives a smooth metallic luster finish and has excellent durability.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Undercoat White and then fill any surface imperfections with Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Metallic Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids : 50 ± 10 %

Colors : All Colors from shade card.

Film Thickness : Dry : 35 ± 5 microns.

Pack Viscosity : 6 – 8 min @ ford cup F4

Specific Gravity : 1 ± 0.1 Depending upon colors

Drying Time at 25°C : 5-6 Hours

Recoat at 25°C : 16 Hours

Practical Coverage : A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI METALLIC ENAMEL

TECHNICAL DATA

Application

:

Spray



Thinning

Conventional Spray

:

Add up to 2 parts of white spirit or petrol to 4 parts of paint (50%)

Cleaning

:

Clean all equipment with white spirit or Kerosene Immediately after use.

Finish

:

Smooth Glossy Finish.

Pack Size

:

0.91Liter, 3.64Liter , 14.56 Liter

Recommended System:

General Steel Surface

- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI Metallic Enamel.

Recommended System:

Galvanized Surface or Non Ferrous

- One coat wash primer
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI Metallic Enamel.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White.
- 2 -3 Coats MOBI Metallic Enamel.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI MATT ENAMEL

Description

MOBI MATT FINISH is an excellent quality paint which protects the surface from water and its vapors. It is washable paint which maintain the beauty of walls, roofs, Wood, Metal, chipboards and hardboards specially bathroom, kitchen and corridors for years.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Undercoat White and then fill any surface imperfections with Putty. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Pigment	:	Non Lead Pigment
Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	All Colors from shade card.
Film Thickness	:	Dry : 35 ± 5 microns.
Pack Viscosity	:	18 – 22 Poise
Specific Gravity	:	1.36 ± 0.1 Depending upon colors
Gloss	:	Maximum 10 Gu
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI MATT ENAMEL

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 2 parts of white spirit to 4 parts of paints (50%).
Conventional Spray	:	Add up to 2 parts of white spirit to 4 parts of paint (50%)
Cleaning	:	Clean all equipment with white spirit or Kerosene Immediately after use.
Finish	:	Smooth Glossy Finish.
Pack Size	:	0.91Liter, 3.64Liter , 14.56 Liter

Recommended System:

General Steel Surface/Non Ferrous

- For Non Ferrous 1 Coat of wash prime .
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI Matt Enamel.

Recommended System:

For Masonry Surface

- One coat Mobi Wall Sealer
- 1-2 coat MOBI Wall Putty
- 2 -3 Coats MOBI Matt Enamel.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White.
- 2 -3 Coats MOBI Matt Enamel.
-

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SYNTHETIC VARNISH

Description

MOBI SYNTHETIC CLEAR VARNISH is based on special resin and solvent mixture. It is a protective coating against humidity, steam lubricating oil mild acids and alkalies. It is suitable for all types of interior and exterior, wood and metal surfaces.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Wood Sealer. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Binder	:	Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	Transparent.
Film Thickness	:	Dry : 25 ± 5 microns.
Pack Viscosity	:	4 – 6 Minutes
Specific Gravity	:	0.90 ± 0.05
Gloss	:	≥ 85 GU
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 140 -200 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI SYNTHETIC VARNISH

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 2 parts of white spirit to 4 parts of paints (50%).
Conventional Spray	:	Add up to 2 parts of white spirit to 4 parts of paint (50%)
Cleaning	:	Clean all equipment with white spirit or Kerosene Immediately after use.
Finish	:	Smooth Glossy Finish.
Pack Size	:	0.25Liter, 0.75 Liter , 3 Liter

Recommended System:

General Steel Surface/Non Ferrous

- For Non Ferrous 1 Coat of wash prime .
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI SYNTHETIC VARNISH.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White/ Mobi Wood Sealer.
- 2 -3 Coats MOBI Synthetic Varnish.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI POLYURETHANE VARNISH GLOSS

Description

MOBI PU Clear Varnish is PU modified alkyd based, pigment free clear varnish, which is suitable for all types of interior & exterior wood and metal surfaces. It provides ultimate protection and durability to Wood and metal surfaces. It is designed to produce a flexible and clear film to protect the substrate against environmental concerns such as ultraviolet light, dirt and moisture. The cured coating is resistant to polymer degradation and yellowing.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Wood Sealer. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Binder	:	Polyurethane Modified Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	Transparent.
Film Thickness	:	Dry : 25 ± 5 microns.
Pack Viscosity	:	160 – 190 Seconds
Specific Gravity	:	0.90 ± 0.05
Gloss	:	≥ 85 GU
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI POLYURETHANE VARNISH GLOSS

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 1 parts of white spirit to 4 parts of paints (25%).
Conventional Spray	:	Add up to 1 parts of white spirit to 4 parts of paint (25%)
Cleaning	:	Clean all equipment with white spirit or Kerosene Immediately after use.
Finish	:	Smooth Glossy Finish.
Pack Size	:	0.75 Liter

Recommended System:

General Steel Surface/Non Ferrous

- For Non Ferrous 1 Coat of wash prime .
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI PU VARNISH.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White/ Mobi Wood Sealer.
- 2 -3 Coats MOBI PU Varnish.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI POLYURETHANE VARNISH MATT

Description

MOBI PU Clear Varnish Matt is PU modified alkyd based, pigment free clear matt varnish, which is suitable for all types of interior & exterior wood and metal surfaces. It provides ultimate protection and durability to Wood and metal surfaces. It is designed to produce a flexible and clear film to protect the substrate against environmental concerns such as ultraviolet light, dirt and moisture. The cured coating is resistant to polymer degradation and yellowing.

SURFACE PREPARATION:

Surfaces must be free from dust, dirt, grease, oil, heavy shoot or chalk. Remove all defective or poorly adhering materials by rubbing down using a suitable abrasive paper or stiff brush.

Metal Surface:

After priming new surfaces with MOBI Red Oxide Primer or Wash primer for nonferrous surface, fill the surface where required with Steel Putty. Please refer to TDS of Mobi Red Oxide Primer for correct application procedure and drying time properties.

Wooden Surface:

Scuff of the surface with suitable abrasive paper than prime the surface with MOBI Wood Sealer. Scuff the surface using suitable abrasive paper and dust off.

TECHNICAL DATA

Composition (Nominal)

Binder	:	Polyurethane Modified Alkyd
Solvent	:	MTT, Kerosene Oil, White Spirit

Volume solids	:	50 ± 10 %
Colors	:	Transparent.
Film Thickness	:	Dry : 25 ± 5 microns.
Pack Viscosity	:	90 – 120 Seconds
Specific Gravity	:	0.90 ± 0.05
Gloss	:	≤ 20 GU
Drying Time at 25°C	:	5-6 Hours
Recoat at 25°C	:	16 Hours
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 140 -170 Square foot /liter/coat.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY




8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI POLYURETHANE VARNISH MATT

TECHNICAL DATA

Application	:	Brush,  Roller  Spray 
Thinning	:	
Brush or Roller	:	Add up to 1 parts of white spirit to 4 parts of paints (25%).
Conventional Spray	:	Add up to 1 parts of white spirit to 4 parts of paint (25%)
Cleaning	:	Clean all equipment with white spirit or Kerosene Immediately after use.
Finish	:	Smooth Glossy Finish.
Pack Size	:	0.75 Liter

Recommended System:

General Steel Surface/Non Ferrous

- For Non Ferrous 1 Coat of wash prime .
- 1-2 coat MOBI red oxide primer
- 2 -3 Coats MOBI PU VARNISH.

Recommended System:

For Wood

- 1-2 coat MOBI Undercoat White/ Mobi Wood Sealer.
- 2 -3 Coats MOBI PU Varnish.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI GLOSS WOOD LACQUER

Description

MOBI GLOSS WOOD LACQUER is especially formulated for application on wooden surface, which provide clear finish with excellent adhesion and durability. Its transparent glossy finish, provides a clear and flexible coating thus enhancing natural beauty of the wood. It's tough and hard film provides excellent resistance to water, tea and beverages stains

SURFACE PREPARATION:

Scuff the surface thoroughly with suitable abrasive paper to remove any wood imperfections. Apply 2 or more coats of Mobi Wood sealer. Let it dry, scuff it with suitable sand paper. 3-4 coats of Mobi Gloss Lacquer.

TECHNICAL DATA

TYPE	:	Single Pack.
Flash Point	:	< 21°C
Specific Gravity	:	0.95 ± 0.05
Color	:	Transparent
Thinning	:	50% to 75% with Mobi Thinner Special
Average Spreading Rate	:	100 ~ 110 Sq. Feet per liter per coat.
Drying Time	:	a. Surface Dry: 10 - 20 minutes @ 30°C b. Recoat : 30 minutes @ 30°C c. Hard Dry : 3 Hours
Application	:	Spray
Number of Coats	:	3 ~ 4 Coats
Finish & Gloss	:	Smooth, Glossy
Thinner	:	Mobi Thinner Special
Packing	:	0.91, 3.64 Liter

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI MATT WOOD LACQUER

Description

MOBI MATT WOOD LACQUER is especially formulated for application on wooden surface, which provide clear finish with excellent adhesion and durability. Its transparent matt finish, provides a clear and flexible coating thus enhancing natural beauty of the wood. It's tough and hard film provides excellent resistance to water, tea and beverages stains

SURFACE PREPARATION:

Scuff the surface thoroughly with suitable abrasive paper to remove any wood imperfections. Apply 2 or more coats of Mobi Wood sealer. Let it dry, scuff it with suitable sand paper. Apply 3-4 coats of Mobi Matt Lacquer.

TECHNICAL DATA

TYPE	:	Single Pack.
Flash Point	:	< 21°C
Specific Gravity	:	0.95 ± 0.05
Color	:	Transparent
Thinning	:	50% to 75% with Mobi Thinner Special
Average Spreading Rate	:	100 ~ 110 Sq. Feet per liter per coat.
Drying Time	:	a. Surface Dry: 10 - 20 minutes @ 30°C b. Recoat : 30 minutes @ 30°C c. Hard Dry : 3 Hours
Application	:	Spray
Number of Coats	:	3 ~ 4 Coats
Finish & Gloss	:	Smooth, Matt
Thinner	:	Mobi Thinner Special
Packing	:	0.91, 3.64 Liter

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI WOOD SEALER

Description

MOBI WOOD SEALER is an NC based premium quality sealer for wood and wood care products. It is an ideal sealer to fill surface imperfections of all kinds of wooden furniture and fixtures. It penetrates into the pores of wood and prevents sinkage of topcoat to allow good hold out.

SURFACE PREPARATION:

Ensure that the wood is dry right through and properly seasoned. Fill the imperfections, grooves, cuts etc. with the filler by matching its color with that of the wood. Thoroughly scuff with coarse abrasive paper to produce a uniform surface. Level out all the surface rock bottom with manual sanding or by using mechanical sander. Thin MOBI Wood Sealer with MOBI Thinner Special. Mix thoroughly and apply two or more coats depending upon surface condition. Allow a gap of 30 minutes in between coats. Let it dry for 3- 4 hours. Scuff the surface with fine sand paper, dust off and petrol wipe before over coating with MOBI Wood Lacquer.

TECHNICAL DATA

TYPE	:	Single Pack.
Flash Point	:	< 21°C
Specific Gravity	:	0.95 ± 0.05
Color	:	Milky & Pale Yellow
Thinning	:	50% to 75% with Mobi Thinner Special
Average Spreading Rate	:	100 ~ 110 Sq. Feet per liter per coat.
Drying Time	:	a. Surface Dry: 10 - 20 minutes @ 30°C b. Recoat : 30 minutes @ 30°C c. Hard Dry : 3 Hours
Application	:	Spray
Number of Coats	:	3 ~ 4 Coats
Finish & Gloss	:	Smooth, Matt
Thinner	:	Mobi Thinner Special
Packing	:	0.91, 3.64 Liter

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI THINNER SPECIAL

Description

MOBI THINNER SPECIAL is especially designed blend of aromatic and aliphatic hydrocarbons that make it a perfect thinner for any nitrocellulose based paint or lacquer. Its balanced formula provides excellent solvent blend for application in all seasons. It provides excellent finish.

TECHNICAL DATA

Color	:	Colorless clear
Nature	:	Solvent
Density	:	0.85 ± 0.05
Volatile Matter	:	99% minimum.
Flash Point	:	< 21° C
Packing	:	0.91 & 3.64 Liters
Storage Stability	:	18 months when stored at 15-30°C in original sealed container.

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI ALLUMINIUM FINISH

Description

MOBI ALUMINIUM PAINT is a silver paint with superior metallic luster to protect surface from corrosion, discolorations and effect of mild heat. Can be used on pipe lines, chimneys, machine, stream pipes, light poles, storage vessels, bridges & oven doors etc.

SURFACE PREPARATION:

Surface must be free from dust, dirt, grease, oil, heavy shoot, chalk, etc. Remove all old flakes, loose paint to avoid adhesion problem. Scuff with suitable emery paper, and dust off with brush. Apply one coat of MOBI Red Oxide Primer with spray, brush or Roller, allow drying, than apply 3 -4 coats Mobi Aluminum Paint.

TECHNICAL DATA

TYPE	:	Single Pack.
Flash Point	:	< 21°C
Specific Gravity	:	01 ± 0.1
Viscosity	:	10 – 16 sec @ ford cup F4
Color	:	Aluminum Silver
Thinning	:	Not Required Ready to use
Average Spreading Rate	:	140 ~ 170 Sq. Feet per liter per coat.
Drying Time	:	a. Surface Dry: 1 - 2 Hours @ 30°C b. Recoat : 12 Hours @ 30°C c. Hard Dry : 20 - 24 Hours
Application	:	Spray ,Brush, Roller
Number of Coats	:	3 ~ 4 Coats
Finish & Gloss	:	Smooth, Glossy
Thinner	:	Mineral Turpentine, White Spirit
Packing	:	0.25,0.91, 3.64 Liter

Safety & Handling Precautions:

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.
- As long as the container is firmly sealed; the material can be kept for 18-Months without deterioration.

Spreading rates are calculated and due allowance for loss and wastage should made. Storage stability 18 months when stored properly in original sealed container at 15-35C. The data is subject to change without notice.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: MOBI PAINT REMOVER

Description

MOBI Paint Remover is supplied in ready to use consistency.

Characteristics & Uses:

Mobi paint remover is a nonflammable high performance paint stripper, designed to remove enamel paints without affecting Aluminum or mild steel substrate.

Application:

Clean the surface with cleaning solvent and then apply paint remover with brush, scraper or spatula and left it for about 30-45 minutes, soon after the paint starts showing wrinkles, it can easily be removed with spatula. On very old painted surfaces a second application of paint remover may be required. After removal of paint the clean metal surface is washed with cold or warm water preferably containing a small quantity of detergent.

TECHNICAL DATA

TYPE	:	Single Pack Ready to use
Recommended Application		
Condition	:	Temperature : 15-35°C Relative Humidity : 35-75%
Odour	:	Mild Odor
Nature	:	Thixotropic.
Density	:	1.18 ± 0.1
Flash Point	:	Above 90 ° C
Corrosion test at 33° C	:	No corrosion observed after 48 Hours on aluminium or mild steel panel.
Storage stability at 15-30° C	:	12 months when stored in original sealed container.
Packing	:	0.75 & 3 Liters

Precaution

- Use protective equipment while application e.g. Apron, Gloves, Protective Glasses and Dust Mask.
- Ensure adequate ventilation during application.
- In case of Eye Splashes, wash with plenty of Fresh Water and consult medical advice.
- In case of skin contact, wash with plenty of water. In case of skin irritation (Sensitive Skin), obtain medical advice.
- In case of ingestion, do not induce vomiting. Drink plenty of Milk/Water and immediately consult a physician.
- Store the product below 40 °C and avoid direct sunlight for a longer period.

Limited Warranty

Since Mobi Paints does not control the application of its products, nor the condition of the surfaces to which they are applied, A limited warranty is provided. If the product do not perform as specified .Mobi paints liability will under no circumstances exceed replacement of product.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: Mobi's Roof Coating -1050

DESCRIPTION

Mobi Roof Coating is a reinforced elastomeric compound based on special Co-Polymer Acrylic Elastomeric Resin. It provides a flexible water proofing membrane, due to its special internal reinforced nature, it will counter small to medium size cracks. The use of very fine particle pigment and highly durable binder provides ultimate water barrier membrane on roofs combined with good dirt pick-up resistance with flexibility and keep the surface cool.

SURFACE PREPARATION:

- Freshly plastered surfaces must be allowed to cure completely. It is recommended to allow at least 28 days for new surfaces for curing.
- Ensure surface is thoroughly clean, dry and free from all loose dirt, chalk, grease, fungi and algae. This can be achieved by brushing with a wire/stiff coir brush, followed by water jetting (if required) and treat the affected area with bleach solution
- Bituminous coating applied prior to this should be scraped off completely.
- Check the surface properly for any loosely held plaster surfaces. Dents and other cracks should be filled using suitable repair mortar. Fill up all minor cracks and defects with s cement and sand mixture in the ratio 1:3. Avoid application of putty or filling compound.
- Ensure uniform slope to the surface.

Application:

- Clean the roof and parapet surface thoroughly as explained above.
- Apply a self-priming coat of Mobi Roof Coating over the dried surface by diluting with water up to 50%.
- Apply first coat of Undiluted or a maximum of 25% diluted Mobi Roof Coating using brush or roller on roof and parapet surface. Allow the surface to dry for 5-6 hours.
- Apply the second coat of Mobi Roof Coating at 90° (angle) to the first coat application.
- Achieving a proper DFT is very important for waterproofing.
- Therefore, achieve a forced coverage of 1.5 – 1.75 m²/l/3 coats.
- If forced coverage is not achieved, apply an additional coat of Mobi Roof Coating.
- Allow the system to cure for 7 days before carrying out any tests.
- To ensure optimum waterproofing performance, the entire roof (including parapets) even if it is a joint parapet wall, drainage slope of the roof and sunken floors will have to be covered with the coating.
- Extra care needs to be taken in areas with joints and water spouts since any crack or fissure of any nature will give rise to ingress of water, which in turn, will deter the desired performance of the coating.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com



Technical Data

Product: Mobi's Roof Coating -1050

TECHNICAL DATA

Type	:	Ready to use.
Composition (Nominal)		
Pigment	:	Non Lead Pigment
Binder	:	Co-Polymer Acrylic Elastomeric Resin.
Solvent	:	Water
Volume solids	:	65 ± 10 %
Colors	:	White only
Film Thickness	:	Wet : 450-900 microns. Dry : 300-600 microns.
Drying Time at 25°C	:	5 - 6 Hours depending upon thickness & Temperature.
Thinner	:	If required use Water as thinner.
Gloss	:	Egg Shell
Over Coat at 25 °C	:	12 Hours.
Practical Coverage	:	A guide to the practical coverage which can be achieved under normal condition is 1.5 – 1.75 Square meter /liter/ 3 coat.

Maintenance:

- Any horizontal surface will have dirt accumulation. In order to maintain/clean the surface, it is essential that only soft cleaning is done.
- Clean the terrace after 3 months to remove the accumulated dust.
- DO NOT use wire brushes or any other hard cleaning tools over the surface painted with Mobi Roof Coating.
- Check for adhesion loss after a year.
- In areas where adhesion loss occurs, remove the coat extending 1 foot. Follow the regular procedure.
- Do not use sharp or pointed objects on the coating as they may rip them off. Normal foot traffic is permissible.
- Do not use strong bleaching agents or acids to clean the surface.
- Overflow pipes for the water tanks need to be grounded properly to ensure the proper water runoff from the surface.

Note:

Recommended spreading rate per liter base upon minimum recommended dry film thickness per coat. No allowance is made for material loss during application. Since Mobi Paints does not control the application of its products, nor the condition of the surfaces to which they are applied, A limited warranty is provided. If the product does not perform as specified. Mobi paints liability will under no circumstances exceed replacement of product.

NEW MUBEEN PAINT INDUSTRIES (Pvt.) Ltd.



ISO 9001:2015 CERTIFIED COMPANY

8-KM Khushab Road, Near Dhrema Sargodha-Pakistan.
Ph: +92-48-3710739- Cell: +92-302-8602213 - +92-344-7473646
E-mail: info@mobipaints.com Website: www.mobipaints.com